



## **APEX® 60002**

## Teknor Apex Company - Flexible Polyvinyl Chloride

Wednesday, August 28, 2019

General Information					
General					
Material Status	Commercial: Active				
Availability	<ul><li> Africa &amp; Middle East</li><li> Asia Pacific</li></ul>	<ul><li>Europe</li><li>Latin America</li></ul>	North America		
Features	Flame Retardant				
Uses	Communication Wire Insulation				
Wire Types	• CL2R • CL3R	• CMR • FPLR	<ul><li>MPR</li><li>OFNR</li></ul>		
Agency Ratings	<ul><li>NEC Article 725</li><li>NEC Article 760</li><li>NEC Article 770</li></ul>	<ul><li>NEC Article 800</li><li>UL 13</li><li>UL 1424</li></ul>	• UL 444		
RoHS Compliance	<ul> <li>RoHS Compliant</li> </ul>				
Appearance	• Opaque				
Forms	• Pellets				
Processing Method	Extrusion				

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.30		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	3500	psi	ASTM D638
Tensile Elongation (Break)	270	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore C, 10 sec)	90		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	14.0	°F	ASTM D746
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	30	%	ASTM D2863
Additional Information			

Temperature Rating: 90 °C

Processing Information			
Extrusion	Nominal Value Unit		
Melt Temperature	390 °F		

## **Notes**

Revision Date: 12/12/2013

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.