



## **APEX® 65001**

## Teknor Apex Company - Flexible Polyvinyl Chloride

Wednesday, August 28, 2019

General Information					
General					
Material Status	Commercial: Active				
Availability	<ul> <li>Africa &amp; Middle East</li> </ul>	• Europe	North America		
	<ul> <li>Asia Pacific</li> </ul>	<ul> <li>Latin America</li> </ul>	• Notur America		
Features	Flame Retardant				
Uses	Communication Wire Jacketing				
Wire Types	• CL2	• CM	• MP		
	• CL3	• FPL	• OFN		
Agency Ratings	NEC Article 725	<ul> <li>NEC Article 800</li> </ul>			
	<ul> <li>NEC Article 760</li> </ul>	• UL 13	• UL 444		
	<ul> <li>NEC Article 770</li> </ul>	• UL 1424			
RoHS Compliance	<ul> <li>RoHS Compliant</li> </ul>				
Appearance	<ul> <li>Opaque</li> </ul>				
Forms	• Pellets				
Processing Method	Extrusion				

ASTM & ISO Properties <sup>1</sup>				
Physical	Nominal Value	Unit	Test Method	
Density / Specific Gravity	1.37		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	3350	psi	ASTM D638	
Tensile Elongation (Break)	260	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore C, 10 sec)	70		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Continuous Use Temperature	167	°F	ASTM D794	
Brittleness Temperature	-22.0	°F	ASTM D746	
Flammability	Nominal Value	Unit	Test Method	
Oxygen Index	32	%	ASTM D2863	
Additional Information				

## **Additional Information**

Non-lead

Formerly 95-A0532A-95 Temperature Rating: 75 °C

UL Sunlight Resistance Recognition: No

Processing Information			
Extrusion	Nominal Value Unit		
Melt Temperature	375 °F		

## **Notes**

Revision Date: 12/12/2013

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.