



APEX[®] 65290

Teknor Apex Company - Flexible Polyvinyl Chloride

Wednesday, August 28, 2019

| General Information | | | | | | |
|---------------------|------------------------------------|-----------------------------------|---------------|--|--|--|
| General | | | | | | |
| Material Status | Commercial: Active | | | | | |
| Availability | Africa & Middle East | Europe | North America | | | |
| | Asia Pacific | Latin America | North America | | | |
| Features | UV Resistant | | | | | |
| Uses | Communication Wire Jacketing | | | | | |
| Wire Types | CL2R | • CMR | • MPR | | | |
| | • CL3R | FPLR | • MPR | | | |
| Agency Ratings | NEC Article 725 | NEC Article 800 | | | | |
| | NEC Article 760 | • UL 13 | • UL 444 | | | |
| | NEC Article 770 | • UL 1424 | | | | |
| RoHS Compliance | RoHS Compliant | | | | | |
| Appearance | Opaque | | | | | |
| Forms | Pellets | | | | | |

| ASTM & ISO Properties ¹ | | | | |
|--------------------------------------|---------------|------|-------------|--|
| Physical | Nominal Value | Unit | Test Method | |
| Density / Specific Gravity | 1.38 | | ASTM D792 | |
| Mechanical | Nominal Value | Unit | Test Method | |
| Tensile Strength (Break) | 3100 | psi | ASTM D638 | |
| Tensile Elongation (Break) | 320 | % | ASTM D638 | |
| Hardness | Nominal Value | Unit | Test Method | |
| Durometer Hardness (Shore C, 10 sec) | 70 | | ASTM D2240 | |
| Thermal | Nominal Value | Unit | Test Method | |
| Continuous Use Temperature | 176 | °F | ASTM D794 | |
| Brittleness Temperature | -22.0 | °F | ASTM D746 | |
| Flammability | Nominal Value | Unit | Test Method | |
| Oxygen Index | 33 | % | ASTM D2863 | |
| Additional Information | | | | |

Data Sheet Applies to Color(s) Listed Below: Natural (0117535)

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 8/9/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.