



APEX® 80842

Teknor Apex Company - Flexible Polyvinyl Chloride

Wednesday, August 28, 2019

General Information					
General					
Material Status	Commercial: Active				
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America		
Features	High Heat Resistance	 Sunlight Resistant (720 hours 	s)		
Uses	 Outdoor Applications 	Wire & Cable Applications	Wire Jacketing		
Agency Ratings	UL QMTT2				
RoHS Compliance	RoHS Compliant				
Appearance	Opaque				
Forms	Pellets				

ASTM & ISO Properties ¹				
Physical	Nominal Value	Unit	Test Method	
Density / Specific Gravity	1.30		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	2400	psi	ASTM D638	
Tensile Elongation (Break)	400	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A, 15 sec)	82		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Continuous Use Temperature	221	°F	ASTM D794	
Brittleness Temperature	-23.8	°F	ASTM D746	
Electrical	Nominal Value	Unit	Test Method	
Volume Resistivity	1.2E+14	ohms∙cm	ASTM D257	
Dielectric Constant			ASTM D150	
1 kHz	5.15			
1 MHz	3.09			
Dissipation Factor			ASTM D150	
1 kHz	0.094			
1 MHz	0.079			
Flammability	Nominal Value	Unit	Test Method	
Oxygen Index	26	%	ASTM D2863	

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 12/3/2015

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.