



## APEX® 80853-B

## Teknor Apex Company - Flexible Polyvinyl Chloride

Wednesday, August 28, 2019

•	<i>y</i>		Troditiooday, riagast 20, 20 to			
General Information						
General						
Material Status	Commercial: Active					
Availability	<ul> <li>Africa &amp; Middle East</li> </ul>	• Europe	North America			
	<ul> <li>Asia Pacific</li> </ul>	<ul> <li>Latin America</li> </ul>	• North America			
Features	<ul> <li>Flame Retardant</li> </ul>	Oil Resistant				
Uses	<ul> <li>Insulation</li> </ul>	<ul> <li>Wire &amp; Cable Applications</li> </ul>				
Wire Types	• TFFN	• THW	• TW			
	• THHN	• THWN	• 1 ٧٧			
Agency Ratings	• UL 1063	• UL 62				
	• UL 1581	• UL 83				
RoHS Compliance	<ul> <li>RoHS Compliant</li> </ul>					
Appearance	<ul> <li>Opaque</li> </ul>					
Forms	<ul> <li>Pellets</li> </ul>					

ASTM & ISO Properties 1				
Physical	Nominal Value	Unit	Test Method	
Density / Specific Gravity	1.31		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	3100	psi	ASTM D638	
Tensile Elongation (Break)	350	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore C, 10 sec)	75		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Continuous Use Temperature	221	°F	ASTM D794	
Brittleness Temperature	-4.00	°F	ASTM D746	
Electrical	Nominal Value	Unit	Test Method	
Volume Resistivity	8.8E+13	ohms·cm	ASTM D257	
Dielectric Constant			ASTM D150	
1 kHz	4.44			
1 MHz	2.96			
Dissipation Factor			ASTM D150	
1 kHz	0.080			
1 MHz	0.19			
Flammability	Nominal Value	Unit	Test Method	
Oxygen Index	27	%	ASTM D2863	

## **Notes**

Revision Date: 12/12/2013

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.