

APEX® 80853-C

Teknor Apex Company - Flexible Polyvinyl Chloride

Wednesday, August 28, 2019

General Information

Product Description

105°C, Non-Lead Stabilized, Insulation

UL Recognized Component Under QMTT2, File # E73402, PVC Insulation Intended for Use in 90°C Wet Locations

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Flame Retardant	• Oil Resistant	
Uses	• Insulation	• Wet Rated Insulation	• Wire & Cable Applications
Wire Types	• MTW • THHN • THW	• THW-2 • THWN • THWN-2	• TW
Agency Ratings	• UL I Oil Rating	• UL QMTT2	
RoHS Compliance	• RoHS Compliant		
Appearance	• Opaque		
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.31		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	3100	psi	ASTM D638
Tensile Elongation (Break)	350	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore C, 10 sec)	71		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	221	°F	ASTM D794
Brittleness Temperature	-2.20	°F	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	3.4E+15	ohms·cm	ASTM D257
Dielectric Strength	880	V/mil	ASTM D149
Dielectric Constant			ASTM D150
1 kHz	4.36		
1 MHz	2.99		
Dissipation Factor			ASTM D150
1 kHz	0.095		
1 MHz	0.058		
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	27	%	ASTM D2863

+135-3858-6433
+188-1699-6168
+852-695-75415

APEX® 80853-C

Teknor Apex Company - Flexible Polyvinyl Chloride

Additional Information

Volume Resistivity, ASTM D257, 23°C: 2.7×10^{15} ohm-cm

Volume Resistivity, ASTM D257, 50°C: 0.339×10^{15} ohm-cm

Oil Rating: 4 days @ 100 C

Oil Rating: 60 days @ 75 C

720 Hour Sunlight Resistant

Data Sheet Applies to Color(s) Listed Below:

Natural (0116200, 011620052)

Natural 14 (0117285)

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 8/9/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.