

# APEX® 86-K264A-NT

Teknor Apex Company - Flexible Polyvinyl Chloride

Wednesday, August 28, 2019

## General Information

### Product Description

Non-Toxic Compound  
 Shore Hardness Measured at 15 sec. Delay  
 ACR @370°F, PSI 22, Die 20/1 Extrusion Time: 57 Seconds

### General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Appearance	• Clear/Transparent		
Forms	• Pellets		
Processing Method	• Injection Molding		

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.21		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2390	psi	ASTM D638
Tensile Elongation (Break)	400	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	77		ASTM D2240

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.