

APEX® RE 8219

Teknor Apex Company - Rigid Polyvinyl Chloride

Thursday, August 29, 2019

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Good Dimensional Stability • Good Melt Strength	• High Impact Resistance • Medium Gloss	
UL File NumberUSA	• QMFZ2 E54709		
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.38		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	406000	psi	ASTM D638
Tensile Strength (Break)	6130	psi	ASTM D638
Flexural Modulus	399000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	19	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 10 sec)	83		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Annealed, 0.125 in	160	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating			
--	•	V-0	UL 94
	•	5VA	
--	•	V-0	CSA
	•	5VA	

Additional Information

Data Sheet Applies to Color(s) Listed Below:

Black 1 (1053928)
 Grey 3187 (1054863)
 Natural (1054835)
 Tan 2216 (1113361)
 Tan 2342 (1135075)
 White 1458 (1068783)

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 8/9/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.