

# APEX® RE 9118A UV

Teknor Apex Company - Rigid Polyvinyl Chloride

Thursday, August 29, 2019

## General Information

### General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Forms	• Pellets		

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.36		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>2</sup>	402000	psi	ASTM D638
Tensile Strength (Break)	7280	psi	ASTM D638
Tensile Elongation (Break)	130	%	ASTM D638
Flexural Modulus <sup>3</sup>	410000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in, Injection Molded)	2.9	ft-lb/in	ASTM D256
Drop Impact Resistance <sup>4</sup> (73°F, 0.500 in)	1.95	in-lb/mil	ASTM D4226
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 10 sec)	82		ASTM D2240

### Additional Information

Deflection Temperature Under Load: 69.2  
 264 psi, Annealed 0.125", °C

Deflection Temperature Under Load: 61.3  
 264 psi, Unannealed 0.125", °C

Flame Rating - UL: Pending

Color - Spectrophotometer: Transparent / slight blue

Haze % - Spectrophotometer: 14.3

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 0.20 in/min

<sup>3</sup> 0.050 in/min

<sup>4</sup> Procedure A

Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.