

APEX® RM 8001R-NT

Teknor Apex Company - Rigid Polyvinyl Chloride

Thursday, August 29, 2019

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.30		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	234000	psi	ASTM D638
Tensile Strength (Break)	5200	psi	ASTM D638
Tensile Elongation (Break)	170	%	ASTM D638
Flexural Modulus	316000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
72°F, 0.125 in, Compression Molded	0.60	ft-lb/in	
Drop Impact Resistance ² (73°F, 0.125 in)	0.800	in-lb/mil	ASTM D4226
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 10 sec)	80		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Annealed)	105	°F	ASTM D648

Additional Information

Gamma Stable

Notes

¹ Typical properties: these are not to be construed as specifications.

² Procedure B, Conical Dart

Revision Date: 12/18/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.