

APEX® RM 8220

Teknor Apex Company - Rigid Polyvinyl Chloride

Thursday, August 29, 2019

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.31		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ² (Compression Molded)	330000	psi	ASTM D638
Tensile Strength ² (Break, Compression Molded)	5800	psi	ASTM D638
Tensile Elongation (Break)	120	%	ASTM D638
Flexural Modulus (Compression Molded)	340000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact 73°F, 0.125 in, Compression Molded	20	ft-lb/in	ASTM D256
Drop Impact Resistance ³ (73°F)	1.30	in-lb/mil	ASTM D4226
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 10 sec)	82		ASTM D2240

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.20 in/min

³ Procedure A, TUP

Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.