



APEX® RM 9012

Teknor Apex Company - Rigid Polyvinyl Chloride

Thursday, August 29, 2019

| General Information | | | | | |
|---------------------|---|--|---------------|--|--|
| General | | | | | |
| Material Status | Commercial: Active | | | | |
| Availability | Africa & Middle East Asia Pacific | EuropeLatin America | North America | | |
| Forms | Pellets | | | | |

| ASTM & ISO Properties ¹ | | | | | |
|--|---------------|-----------|-------------|--|--|
| Physical | Nominal Value | Unit | Test Method | | |
| Density / Specific Gravity | 1.46 | | ASTM D792 | | |
| Mechanical | Nominal Value | Unit | Test Method | | |
| Tensile Modulus ² | 463000 | psi | ASTM D638 | | |
| Tensile Strength ² (Break) | 6320 | psi | ASTM D638 | | |
| Tensile Elongation (Break) | 35 | % | ASTM D638 | | |
| Flexural Modulus ³ | 380000 | psi | ASTM D790 | | |
| Impact | Nominal Value | Unit | Test Method | | |
| Notched Izod Impact (73°F, 0.125 in, Injection Molded) | 12 | ft·lb/in | ASTM D256 | | |
| Drop Impact Resistance ⁴ (73°F) | 2.50 | in·lb/mil | ASTM D4226 | | |
| Hardness | Nominal Value | Unit | Test Method | | |
| Durometer Hardness (Shore D, 10 sec) | 82 | | ASTM D2240 | | |
| Thermal | Nominal Value | Unit | Test Method | | |
| Deflection Temperature Under Load | | | ASTM D648 | | |
| 264 psi, Annealed, 0.250 in | 159 | °F | | | |

Notes

Revision Date: 12/12/2013

¹ Typical properties: these are not to be construed as specifications.

² 0.20 in/min

³ 0.050 in/min

⁴ Procedure A, TUP