



FIREGUARD® 910-FOB-NL1

Teknor Apex Company - Flexible Polyvinyl Chloride

Wednesday, August 28, 2019

General Information					
General					
Material Status	Commercial: Active				
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America		
Uses	 Plenum Cable Jacketing 	Wire & Cable Applications			
Agency Ratings	• UL QMTM2				
Forms	Pellets				

ASTM & ISO Properties ¹				
Physical	Nominal Value	Unit	Test Method	
Density / Specific Gravity	1.60		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	2500	psi	ASTM D638	
Tensile Elongation (Break)	200	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore C, 10 sec)	83		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Continuous Use Temperature	167	°F	ASTM D794	
Brittleness Temperature	17.6	°F	ASTM D746	
Electrical	Nominal Value	Unit	Test Method	
Dielectric Strength	770	V/mil	ASTM D149	
Dielectric Constant			ASTM D150	
1 kHz	4.65			
1 MHz	3.59			
Dissipation Factor			ASTM D150	
1 kHz	0.083			
1 MHz	0.035			
Flammability	Nominal Value	Unit	Test Method	
Oxygen Index	42	%	ASTM D2863	

Additional Information

Dynamic Heat Stability @ 205C, 100 RPM, 72 gr.#5 Bowl (Min.s to decomposition) - 57

Kayeness ACR @350F, 1000 sec -1 (Pa-sec) = 290

Cone Calorimeter @ 75 kW/m2

Peak Heat Release Rate (kw/m2) = 111

Avg. Heat Release Rate (kw/m2) = 60

Total Heat Released (MJ/m2) = 77

Avg. Heat of Combustion (MJ/kg) = 13.5

Avg. Specification Extinction Area (m2/kg) = 325

Peak Smoke (i/m) = 2.3

Data Sheet Applies to Color(s) Listed Below: Natural (0129825, 012982551, 012982552)

Notes

Revision Date: 8/13/201

¹ Typical properties: these are not to be construed as specifications.