



FIREGUARD® 910-L16-C6-NL2

Teknor Apex Company - Flexible Polyvinyl Chloride

Wednesday, August 28, 2019

General Information					
General					
Material Status	Commercial: Active				
Availability	Africa & Middle EastAsia Pacific	EuropeLatin America	North America		
Uses	 Plenum Cable Jacketing 	Wire & Cable Applications			
Agency Ratings	• UL QMTM2				
RoHS Compliance	 RoHS Compliant 				
Forms	Pellets				

ASTM & ISO Properties 1				
Physical	Nominal Value	Unit	Test Method	
Density / Specific Gravity	1.65		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	1800	psi	ASTM D638	
Tensile Elongation (Break)	200	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness			ASTM D2240	
Shore C	88			
Shore C, 10 sec	81			
Thermal	Nominal Value	Unit	Test Method	
Continuous Use Temperature	167	°F	ASTM D794	
Brittleness Temperature	-4.00	°F	ASTM D746	
Electrical	Nominal Value	Unit	Test Method	
Dielectric Constant (1 MHz)	3.73		ASTM D150	
Dissipation Factor (1 MHz)	0.042		ASTM D150	
Flammability	Nominal Value	Unit	Test Method	
Oxygen Index	45	%	ASTM D2863	

Additional Information

Av.Sp. Extinction Area: 262 m²/kg Avg. Heat of Combustion: 12.54 MJ/kg Avg. Heat Rel. Rate: 67 kw/m²

Dynamic Heat Stability, 205°C, 100 rpm, 72 gms: 44 Kayeness ACR, 370°F, 1000 sec-1: 417 PA-sec

Peak Heat Rel. Rate: 111 kw/m²

Peak Smoke: 1.1

Specific Gravity, ASTM D792: 1.63 to 1.67 sp gr 23/23°C

TA Six Digit Description: 116-474 Total Heat Rel'd: 62 MJ/m²

Notes

Revision Date: 12/12/2013

¹ Typical properties: these are not to be construed as specifications.