

FIREGUARD® 910L16-C1A-NL1

Teknor Apex Company - Flexible Polyvinyl Chloride

Wednesday, August 28, 2019

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Flame Retardant • Low Smoke Emission		
Uses	• Plenum Cable Jacketing		
Wire Types	• CL2P • CL3P	• CMP • FPLP	• MPP • OFNP
Agency Ratings	• NEC Article 725 • NEC Article 760 • NEC Article 770	• NEC Article 800 • UL 13 • UL 1424	• UL 1651 • UL 444 • UL QMTM2
RoHS Compliance	• RoHS Compliant		
Appearance	• Opaque		
Forms	• Pellets		
Processing Method	• Extrusion		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.62		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2100	psi	ASTM D638
Tensile Elongation (Break)	270	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore C	89		
Shore C, 10 sec	80		
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	167	°F	ASTM D794
Brittleness Temperature	-13.0	°F	ASTM D746
Electrical	Nominal Value	Unit	Test Method
Dielectric Constant			ASTM D150
1 kHz	4.56		
1 MHz	3.58		
Dissipation Factor			ASTM D150
1 kHz	0.065		
1 MHz	0.038		
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	51	%	ASTM D2863

+135-3858-6433
+188-1699-6168
+852-695-75415

FIREGUARD® 910L16-C1A-NL1

Teknor Apex Company - Flexible Polyvinyl Chloride

Additional Information

Av.Sp. Extinction Area: 316 m²/kg
Avg. Heat of Combustion: 10.3 MJ/kg
Avg. Heat Rel. Rate: 69 kw/m²
Dynamic Heat Stability, 205°C, 100 rpm, 72 gms: 34
Kayeness ACR, 370°F, 1000 sec-1: 315 PA-sec
Kayeness ACR, 370°F, 100 sec-1: 1243 PA-sec
Peak Heat Rel. Rate: 120 kw/m²
Peak Smoke: 1.91 l/m
TA Six Digit Description: 0112654
Total Heat Rel'd: 65 MJ/m²

Processing Information

Extrusion	Nominal Value	Unit
Melt Temperature	380	°F

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.