

FLEXALLOY® 35022RV-60NT CBL B8 NP

Teknor Apex Company - Flexible Polyvinyl Chloride

Wednesday, August 28, 2019

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• BPA Free • E-beam Sterilizable • Ethylene Oxide Sterilizable	• Latex Free • No Animal Derived Components • Non-Phthalate - Citrate Plasticizer	• Non-Phthalate Plasticizer • Radiation (Gamma) Resistant • Radiation Sterilizable
Agency Ratings	• EC 1907/2006 (REACH)	• OEHHA (California) Proposition 65	
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.20		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
50% Strain	375	psi	
100% Strain	650	psi	
300% Strain	1520	psi	
Tensile Strength (Break)	2090	psi	ASTM D638
Tensile Elongation (Break)	400	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 15 sec, Operating Stand	55		
Shore A, 15 sec, Hand Held	60		

+135-3858-6433
+188-1699-6168
+852-695-75415

FLEXALLOY® 35022RV-60NT CBL B8 NP

Teknor Apex Company - Flexible Polyvinyl Chloride

Additional Information

EXAMPLE EXTRUSION APPLICATIONS

Blood Pressure Tubing
Blood Transport & Delivery
Bubble Tubing
Cable Jacketing
Catheters
Dialysis Tubing
Drainage Tubing
Endotracheal Airway Tubing
Enteral Feeding Systems
Infusion Tubing
Oxygen Tubing
Peristaltic Pump Tubing
Suction Tubing

EXAMPLE INJECTION MOLDING APPLICATIONS

Adaptors
Blood Pressure Bulbs
Canulae
Caps
Connectors
Drip/Sight Chambers
Ear Protection
Endotracheal Airway Cuffs
Luers
Mouthpieces
Oxygen Masks
Personal Safety Goggles
Resuscitation Bags
Suction Bulbs
Syringe Bulbs
Valves

Data Sheet Applies to Color(s) Listed Below:
Clear Blue B8 NP (1136613)

Processing Information

Extrusion	Nominal Value	Unit
Melt Temperature	350 to 365	°F

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 8/9/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.