

# FLEXALLOY® 35033RV-40NT1 CBL B8 NP

Teknor Apex Company - Flexible Polyvinyl Chloride

Wednesday, August 28, 2019

## General Information

### General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• BPA Free • E-beam Sterilizable • Ethylene Oxide Sterilizable	• Latex Free • No Animal Derived Components • Non-Phthalate - TOTM Plasticizer	• Non-Phthalate Plasticizer • Radiation (Gamma) Resistant • Radiation Sterilizable
Agency Ratings	• EC 1907/2006 (REACH)	• OEHHA (California) Proposition 65	
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Extrusion	• Injection Molding	

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.11		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
50% Strain	155	psi	
100% Strain	300	psi	
300% Strain	760	psi	
Tensile Strength (Break)	1090	psi	ASTM D638
Tensile Elongation (Break)	440	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 15 sec, Operating Stand	35		
Shore A, 15 sec, Hand Held	40		

Revision Date: 8/9/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

**+135-3858-6433**  
**+188-1699-6168**  
**+852-695-75415**

# FLEXALLOY® 35033RV-40NT1 CBL B8 NP

## Teknor Apex Company - Flexible Polyvinyl Chloride

### Additional Information

#### EXAMPLE EXTRUSION APPLICATIONS

Blood Pressure Tubing  
Blood Transport & Delivery  
Bubble Tubing  
Cable Jacketing  
Catheters  
Dialysis Tubing  
Drainage Tubing  
Endotracheal Airway Tubing  
Enteral Feeding Systems  
Infusion Tubing  
Oxygen Tubing  
Peristaltic Pump Tubing  
Suction Tubing

#### EXAMPLE INJECTION MOLDING APPLICATIONS

Adaptors  
Blood Pressure Bulbs  
Canulae  
Caps  
Connectors  
Drip/Sight Chambers  
Ear Protection  
Endotracheal Airway Cuffs  
Luers  
Mouthpieces  
Oxygen Masks  
Personal Safety Goggles  
Resuscitation Bags  
Suction Bulbs  
Syringe Bulbs  
Valves

Data Sheet Applies to Color(s) Listed Below:  
Clear Blue B8 NP (1136628)

### Processing Information

Extrusion	Nominal Value	Unit
Melt Temperature	335 to 350	°F

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

Revision Date: 8/9/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.