

FLEXALLOY® 9200-45-BL

Teknor Apex Company - Polyvinyl Chloride Elastomer

Saturday, August 24, 2019

General Information					
General					
Material Status	Commercial: Active				
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America		
Features	FoamableGood Thermal Stability	 Recyclable Material Ultra High Molecular Weight	Weather Resistant		
Uses	• Foam	• Footwear			
Forms	Pellets				
Processing Method	Extrusion	Injection Molding			

+135-3858-6433 +188-1699-6168 +852-695-75415

ASTM & ISO Properties ¹					
Physical	Nominal Value	Unit	Test Method		
Density / Specific Gravity	1.10		ASTM D792		
Molding Shrinkage - Flow	0.010 to 0.025	in/in	ASTM D955		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Break)	1250	psi	ASTM D638		
Tensile Elongation (Break)	390	%	ASTM D638		
Hardness	Nominal Value	Unit	Test Method		
Durometer Hardness (Shore A, 15 sec)	45		ASTM D2240		
Thermal	Nominal Value	Unit	Test Method		
Brittleness Temperature	-68.8	°F	ASTM D746		

Processing Information				
Injection	Nominal Value	Unit		
Suggested Max Regrind	20	%		
Rear Temperature	320 to 350	°F		
Middle Temperature	320 to 350	°F		
Front Temperature	320 to 350	°F		
Mold Temperature	75 to 125	°F		
Back Pressure	50.0 to 150	psi		
Screw L/D Ratio	20.0:1.0 to 24.0:1.0			
Screw Compression Ratio	2.0:1.0 to 3.0:1.0			

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 12/12/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.