



FLEXALLOY® 9300-60

Teknor Apex Company - Polyvinyl Chloride Elastomer

Saturday, August 24, 2019

General Information					
General					
Material Status	Commercial: Active				
Availability	Africa & Middle EastAsia Pacific	EuropeLatin America	North America		
Features	 Good Thermal Stability Oil Resistant	Recyclable MaterialUltra High Molecular Weight	Weather Resistant		
Uses	Coating ApplicationsHose	SealsTool/Tote Box	• Tubing		
Forms	• Pellets				
Processing Method	 Extrusion 	Injection Molding			

ASTM & ISO Properties 1				
Physical	Nominal Value	Unit	Test Method	
Density / Specific Gravity	1.22		ASTM D792	
Molding Shrinkage - Flow	0.010 to 0.025	in/in	ASTM D955	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (100% Strain)	680	psi	ASTM D638	
Tensile Strength (Break)	2150	psi	ASTM D638	
Tensile Elongation (Break)	340	%	ASTM D638	
Elastomers	Nominal Value	Unit	Test Method	
Compression Set (73°F)	32	%	ASTM D395	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A, 15 sec)	60		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Brittleness Temperature	-45.4	°F	ASTM D746	

Processing Information				
Injection	Nominal Value	Unit		
Suggested Max Regrind	20	%		
Rear Temperature	350 to 380	°F		
Middle Temperature	350 to 380	°F		
Front Temperature	350 to 380	°F		
Mold Temperature	75 to 125	°F		
Back Pressure	50.0 to 150	psi		
Screw L/D Ratio	20.0:1.0 to 24.0:1.0			
Screw Compression Ratio	2.0:1.0 to 3.0:1.0			

Notes

Revision Date: 12/12/2013

¹ Typical properties: these are not to be construed as specifications.