



## **FLEXALLOY® 9601-72**

## Teknor Apex Company - Polyvinyl Chloride Elastomer

Saturday, August 24, 2019

|                 | General Information   |  |                   |  |  |
|-----------------|---|--|-------------------|--|--|
| General         |   |  |                   |  |  |
| Material Status | Commercial: Active  |  |                   |  |  |
| Availability    | <ul><li> Africa &amp; Middle East</li><li> Asia Pacific</li></ul> | <ul><li>Europe</li><li>Latin America</li></ul>                                       | North America     |  |  |
| Features        | <ul><li>Flame Retardant</li><li>High Heat Resistance</li></ul>    | <ul><li>Low Temperature Flexibility</li><li>Sunlight Resistant (720 hours)</li></ul> |                   |  |  |
| Uses            | <ul> <li>Cable Jacketing</li> </ul>                               |  |                   |  |  |
| Wire Types      | • SEOW<br>• SEW   | • SJEOW<br>• SJEW  | • STEOW<br>• STEW |  |  |
| Agency Ratings  | <ul><li>UL Class 11</li><li>UL Class 12</li></ul>                 | <ul><li>UL Class 36</li><li>UL Class 43</li></ul>                                    | • UL QMTT2        |  |  |
| RoHS Compliance | <ul> <li>RoHS Compliant</li> </ul>                                |  |                   |  |  |
| Appearance      | Opaque  |  |                   |  |  |
| Forms           | Pellets   |  |                   |  |  |

| ASTM & ISO Properties <sup>1</sup>   |               |      |             |  |
|--------------------------------------|---------------|------|-------------|--|
| Physical                             | Nominal Value | Unit | Test Method |  |
| Density / Specific Gravity           | 1.25          |      | ASTM D792   |  |
| Mechanical                           | Nominal Value | Unit | Test Method |  |
| Tensile Strength (Break)             | 2100          | psi  | ASTM D638   |  |
| Tensile Elongation (Break)           | 330           | %    | ASTM D638   |  |
| Hardness                             | Nominal Value | Unit | Test Method |  |
| Durometer Hardness (Shore A, 15 sec) | 72            |      | ASTM D2240  |  |
| Thermal                              | Nominal Value | Unit | Test Method |  |
| Continuous Use Temperature           | 221           | °F   | ASTM D794   |  |
| Brittleness Temperature              | -58.0         | °F   | ASTM D746   |  |
| Electrical                           | Nominal Value | Unit | Test Method |  |
| Dielectric Constant                  |               |      | ASTM D150   |  |
| 1 kHz                                | 6.19          |      |             |  |
| 1 MHz                                | 4.08          |      |             |  |
| Dissipation Factor                   |               |      | ASTM D150   |  |
| 1 kHz                                | 0.12          |      |             |  |
| 1 MHz                                | 0.10          |      |             |  |
| Flammability                         | Nominal Value | Unit | Test Method |  |
| Oxygen Index                         | 26            | %    | ASTM D2863  |  |

## **Notes**

Revision Date: 12/12/2013

<sup>&</sup>lt;sup>1</sup> Typical properties: these are not to be construed as specifications.