



FLEXALLOY® 9602-72FR

Teknor Apex Company - Polyvinyl Chloride Elastomer

Sunday, August 25, 2019

General Information					
General					
Material Status	Commercial: Active				
Availability	 Africa & Middle East 	• Europe	North America		
	 Asia Pacific 	 Latin America 	• North America		
Features	Flame Retardant	 Low Temperature Flexibility 			
	 High Heat Resistance 	 Sunlight Resistant (720 hours) 			
Uses	 Cable Jacketing 				
Wire Types	• SCE	• SEW	• STEOW		
	• SE	• SJEOW	• STEW		
	• SEOW	• SJEW	• VW-1		
Agency Ratings	UL Class 11	• UL Class 36	• UL QMTT2		
	• UL Class 12	• UL Class 43	• UL QIVITIZ		
RoHS Compliance	 RoHS Compliant 				
Appearance	Opaque				
Forms	Pellets				

ASTM & ISO Properties 1				
Physical	Nominal Value	Unit	Test Method	
Density / Specific Gravity	1.29		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	1930	psi	ASTM D638	
Tensile Elongation (Break)	390	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A, 15 sec)	72		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Continuous Use Temperature	221	°F	ASTM D794	
Brittleness Temperature	-54.4	°F	ASTM D746	
Electrical	Nominal Value	Unit	Test Method	
Dielectric Constant			ASTM D150	
1 kHz	6.16			
1 MHz	4.10			
Dissipation Factor			ASTM D150	
1 kHz	0.11			
1 MHz	0.11			
Flammability	Nominal Value	Unit	Test Method	
Oxygen Index	30	%	ASTM D2863	

Additional Information

Data Sheet Applies to Color(s) Listed Below:

Black 14 (0112473)

Grey 3240-14 (1094930)

Natural (0111977)

Natural 14 (0112458)

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 8/13/2019