



FLEXALLOY® 9606-65

Teknor Apex Company - Polyvinyl Chloride Elastomer

Sunday, August 25, 2019

General Information							
General							
Material Status	Commercial: Active						
Availability	 Africa & Middle East Asia Pacific	EuropeLatin America	North America				
Features	Flame RetardantHigh Heat Resistance	Low Temperature FlexibilitySunlight Resistant (720 hours)					
Uses	 Cable Jacketing 						
Wire Types	• SEOW • SEW	SJEOWSJEW	• STEOW • STEW				
Agency Ratings	UL Class 11UL Class 12	UL Class 36UL Class 43	• UL QMTT2				
RoHS Compliance	 RoHS Compliant 						
Appearance	Opaque						
Forms	• Pellets						

ASTM & ISO Properties ¹				
Physical	Nominal Value	Unit	Test Method	
Density / Specific Gravity	1.23		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	2100	psi	ASTM D638	
Tensile Elongation (Break)	390	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore A, 15 sec)	65		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Continuous Use Temperature	221	°F	ASTM D794	
Brittleness Temperature	-61.6	°F	ASTM D746	
Electrical	Nominal Value	Unit	Test Method	
Dielectric Constant			ASTM D150	
1 kHz	6.01			
1 MHz	3.87			
Dissipation Factor			ASTM D150	
1 kHz	0.075			
1 MHz	0.11			
Flammability	Nominal Value	Unit	Test Method	
Oxygen Index	26	%	ASTM D2863	

Additional Information

Data Sheet Applies to Color(s) Listed Below:

Natural (0115094)

Notes

Revision Date: 8/13/2019

¹ Typical properties: these are not to be construed as specifications.