

Sinvicomp DBS3607

Teknor Apex Asia Pacific PTE. LTD. - Rigid Polyvinyl Chloride

Thursday, August 29, 2019

General Information

General

| | |
|-------------------|--------------------------|
| Material Status | • Commercial: Active |
| Availability | • Asia Pacific |
| Features | • Good Impact Resistance |
| Uses | • Piping |
| RoHS Compliance | • RoHS Compliant |
| Forms | • Powder |
| Processing Method | • Extrusion |

ASTM & ISO Properties ¹

| Physical | Nominal Value | Unit | Test Method |
|--|---------------|----------|-------------|
| Density / Specific Gravity | 1.44 | | ASTM D792 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Strength ² (Yield) | 7110 | psi | ASTM D638 |
| Tensile Elongation (Break) | 50 | % | ASTM D638 |
| Impact | Nominal Value | Unit | Test Method |
| Notched Izod Impact | 1.1 | ft-lb/in | ASTM D256 |
| Thermal | Nominal Value | Unit | Test Method |
| Vicat Softening Temperature | 203 | °F | ASTM D1525 |
| Thermal Stability ³ (374°F) | > 30 | min | BS 2782 |

Notes

¹ Typical properties: these are not to be construed as specifications.

² 9.8 in/min

³ Congo Red

Revision Date: 9/30/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.