

Sinvicomp SBF3715

Teknor Apex Asia Pacific PTE. LTD. - Rigid Polyvinyl Chloride

Thursday, August 29, 2019

General Information

Product Description

"Sinvicomp" SBF 3715 is a tin-based blown film grade polyvinylchloride resin available in granular form. SBF 3715 provide good performance suitable for shrink wrap film.

"Sinvicomp" SBF 3715 resin contain ingredients that are non-toxic and have been approved for food applications by internationally recognized bodies.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Features	• Food Contact Acceptable
Uses	• Shrink Wrap
Forms	• Pellets
Processing Method	• Blow Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.28 to 1.32		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/21.6 kg)	17	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	4550	psi	ASTM D638
Tensile Elongation (Break)	150	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	0.55	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	70		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	158	°F	ASTM D1525

Additional Information

Typical temperature profile for processing SINVICOMP compound is from 160°C to 180°C. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP.

Feeding zone: 160°C

Compression zone: 160°C~170°C

Mixing zone: 170°C~180°C

Nozzle/Die Zone: 180°C

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 7/4/2014

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.