

Sinvicomp SFR5800C2

Teknor Apex Asia Pacific PTE. LTD. - Rigid Polyvinyl Chloride

Thursday, August 29, 2019

General Information

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific		
Features	• Foamable		
Uses	• Foam	• Profiles	
Forms	• Pellets		
Processing Method	• Extrusion		

ASTM & ISO Properties ¹

Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	31900	psi	ISO 178
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	167	°F	ASTM D1525
Thermal Stability ² (356°F)	> 1	hr	ASTM D2115-92

Notes

¹ Typical properties: these are not to be construed as specifications.

² Congo Red

Revision Date: 1/1/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.