

# Sinvicomp SGH7000

Teknor Apex Asia Pacific PTE. LTD. - Flexible Polyvinyl Chloride

Thursday, August 29, 2019

## General Information

### Product Description

"Sinicomvp" SGH 7000D is a extrusion grade polyvinylchloride compound available in pellet form.

### General

|                   |                      |
|-------------------|----------------------|
| Material Status   | • Commercial: Active |
| Availability      | • Asia Pacific       |
| Uses              | • Garden Hose        |
| Forms             | • Pellets            |
| Processing Method | • Extrusion          |

## ASTM & ISO Properties <sup>1</sup>

| Physical                                | Nominal Value | Unit | Test Method   |
|---|---------------|------|---------------|
| Density / Specific Gravity              | 1.21          |      | ASTM D792     |
| Mechanical                              | Nominal Value | Unit | Test Method   |
| Tensile Strength <sup>2</sup> (Break)   | 1890          | psi  | IEC 60811-1-1 |
| Tensile Elongation <sup>2</sup> (Break) | 360           | %    | IEC 60811-1-1 |
| Hardness                                | Nominal Value | Unit | Test Method   |
| Durometer Hardness (Shore A)            | 65            |      | ASTM D2240    |
| Thermal                                 | Nominal Value | Unit | Test Method   |
| Thermal Stability <sup>3</sup> (374°F)  | > 30          | min  | BS 2782       |

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 9.8 in/min

<sup>3</sup> Congo Red

Revision Date: 1/9/2018

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.