

Sinvicomp SIC3704BUV

Teknor Apex Asia Pacific PTE. LTD. - Rigid Polyvinyl Chloride

Thursday, August 29, 2019

General Information

Product Description

"Sinvicomp" SIC 3704BUV is an extrusion grade polyvinylchloride compound available in pellet form. SIC 3704BUV provides medium impact performance suitable for transparent profiles that need reasonable UV resistance.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Features	• Medium Impact Resistance
Uses	• Labels • Rigid Packaging
Forms	• Pellets
Processing Method	• Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.33		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	5080	psi	ASTM D638
Tensile Elongation (Break)	150	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	0.92	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	167	°F	ASTM D1525

Additional Information

Typical temperature profile for processing SINVICOMP compound is from 160°C to 180°C. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP.

Feeding zone: 160°C

Compression zone: 160°C~170°C

Mixing zone: 170°C~180°C

Nozzle/Die Zone: 180°C

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 7/30/2014

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.