## +135-3858-6433 +188-1699-6168 +852-695-75415

## Sinvicomp SIC3705H

Teknor Apex Asia Pacific PTE. LTD. - Rigid Polyvinyl Chloride

Thursday, August 29, 2019

General Information				
General				
Material Status	Commercial: Active			
Availability	Asia Pacific			
Features	Good Processability	Medium Impact Resistance		
Uses	Rigid Packaging	Tubing		
Forms	Pellets			
Processing Method	Extrusion			

ASTM & ISO Properties <sup>1</sup>				
Physical	Nominal Value	Unit	Test Method	
Density / Specific Gravity	1.33		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength <sup>2</sup> (Yield)	4980	psi	ASTM D638	
Tensile Elongation <sup>2</sup> (Break)	150	%	ASTM D638	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact	0.92	ft·lb/in	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Vicat Softening Temperature	167	°F	ASTM D1525	

## Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 9.8 in/min

Revision Date: 1/2/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.