



Sinvicomp SIZ4505W

Teknor Apex Asia Pacific PTE. LTD. - Flexible Polyvinyl Chloride

Thursday, August 29, 2019

General Information			
General			
Material Status	Commercial: Active		
Availability	Asia Pacific		
Features	Oil Resistant		
Uses	Appliance Wire Insulation		
RoHS Compliance	RoHS Compliant		
Forms	• Pellets		
Processing Method	Extrusion		

ASTM & ISO Properties 1				
Physical	Nominal Value	Unit	Test Method	
Density / Specific Gravity	1.32		ASTM D792	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength (Break)	3050	psi	ASTM D638	
Tensile Elongation (Break)	300	%	ASTM D638	
Hardness	Nominal Value	Unit	Test Method	
Durometer Hardness (Shore D)	44		ASTM D2240	
Thermal	Nominal Value	Unit	Test Method	
Continuous Use Temperature ²	221	°F	ASTM D794	
Electrical	Nominal Value	Unit	Test Method	
Volume Resistivity (68°F)	1.0E+15	ohms·cm	BS 2782 230A	
Flammability	Nominal Value	Unit	Test Method	
Oxygen Index	28	%	ASTM D2863	

Additional Information

Typical temperature profile for PVC compound is from 150°C to 190°C. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP materials.

Feeding zone: 150°C~165°C Mixing zone: 170°C~185°C Metering zone: 180°C~190°C Nozzle/Die Zone: 180°C~190°C

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 1/2/2013

² Dry