

Sinvicomp SIZ4801

Teknor Apex Asia Pacific PTE. LTD. - Flexible Polyvinyl Chloride

Thursday, August 29, 2019

General Information

Product Description

"Sinvicomp" SIZ 4801 is a wire & cable polyvinylchloride compound available in pellet form. SIZ 4801 provides good performance for insulation of electrical wires.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Uses	• Insulation
Wire Types (BS 6746)	• TI1 • TI2
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity ²	1.49		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	2470	psi	IEC 60811-1-1
Tensile Elongation (Break)	200	%	IEC 60811-1-1
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	91		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Heat Stability (392°F)	1.5	hr	BS 2782
Aging	Nominal Value	Unit	Test Method
Mechanical Properties After Aging in Air Oven, 176°F, 168 hr ³			IEC 811-1-2
Change in Tensile Elongation	12	%	
Change in Tensile Strength	10	%	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (68°F)	1.0E+14	ohms·cm	BS 2782
Additional Information	Nominal Value	Unit	Test Method
Loss of Mass - 7 days, 80±2°C ⁴ (176°F)	1.20	mg/cm ²	IEC 811-3-2
Typical temperature profile for processing SINVICOMP compound is from 160°C to 180°C. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP.			

Feeding zone: 160°C
 Compression zone: 160°C~170°C
 Mixing zone: 170°C~180°C
 Nozzle/Die Zone: 180°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² @23°C

³ 80±2°C

⁴ 7 days, 80±2°C

Revision Date: 5/5/2014

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.