

# Sinvicomp SRF1707S

Teknor Apex Asia Pacific PTE. LTD. - Rigid Polyvinyl Chloride

Thursday, August 29, 2019

## General Information

### Product Description

"Sinvicomp" SRF 1707S is an injection molding grade polyvinylchloride compound available in pellet form. SRF 1707S provides normal impact performance suitable for rigid pipes fittings, electrical sockets and couplings.

### General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Features	• Medium Impact Resistance
Uses	• Electrical Parts • Fittings
Forms	• Pellets
Processing Method	• Injection Molding

## ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.48		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	6540	psi	ASTM D638
Tensile Elongation (Break)	110	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	1.6	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	199	°F	ASTM D1525
Heat Stability - (Congo Red @190°C)	30.0	min	BS 2782

### Additional Information

Typical temperature profile for processing SINVICOMP compound is from 160oC to 180oC. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP.

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

Revision Date: 7/23/2018

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.