

Sinvicomp SRF9702/C

Teknor Apex Asia Pacific PTE. LTD. - Rigid Polyvinyl Chloride

Thursday, August 29, 2019

General Information

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Features	• Medium Impact Resistance
Uses	• Electrical/Electronic Applications
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.40		ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/21.6 kg)	17	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	8390	psi	ASTM D638
Tensile Elongation (Break)	40	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	0.73	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness	76		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	187	°F	ASTM D1525 ²
Heat Stability ³ (374°F)	30.0		BS 2782

Notes

¹ Typical properties: these are not to be construed as specifications.

² Loading 1 (10 N)

³ Congo Red

Revision Date: 1/2/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.