

Sinvicomp SRP3704UV

TEKNOR APEX

Teknor Apex Asia Pacific PTE. LTD. - Rigid Polyvinyl Chloride

Thursday, August 29, 2019

General Information					
General					
Material Status	Commercial: Active				
Availability	Asia Pacific				
Features	Medium Impact Resistance				
Uses	Conduit	Piping	Profiles		
Forms	Granules				
Processing Method	 Extrusion 				

ASTM & ISO Properties ¹					
Physical	Nominal Value	Unit	Test Method		
Density / Specific Gravity	1.37 to 1.41		ASTM D792		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Strength (Yield)	6380	psi	ASTM D638		
Tensile Elongation (Break)	110	%	ASTM D638		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact	2.8	ft·lb/in	ASTM D256		
Thermal	Nominal Value	Unit	Test Method		
Vicat Softening Temperature	190	°F	ASTM D1525		

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 8/21/2013

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.