

Sinvicomp SSH5569

Teknor Apex Asia Pacific PTE. LTD. - Flexible Polyvinyl Chloride

Thursday, August 29, 2019

General Information

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Features	• Good Flexibility
Uses	• Cable Jacketing • Wire & Cable Applications
Wire Types	• ST1
Agency Ratings	• IEC 60502
Forms	• Pellets
Processing Method	• Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.44		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	2180	psi	IEC 811-1-1
Tensile Elongation ² (Break)	250	%	IEC 811-1-1
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	82		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Thermal Stability ³ (374°F)	> 2	hr	BS 2782
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength (212°F, 168 hr)	15	%	IEC 811-1-2
Change in Ultimate Elongation (212°F, 168 hr)	20	%	IEC 811-1-2

Notes

¹ Typical properties: these are not to be construed as specifications.

² 9.8 in/min

³ Congo Red

Revision Date: 8/30/2016

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.