

Sinvicomp TAZ42018CMX5

Teknor Apex Asia Pacific PTE. LTD. - Flexible Polyvinyl Chloride

Thursday, August 29, 2019

General Information

Product Description

"Sinvicomp" TAZ42018CMX5 is a wire & cable polyvinylchloride compound available in pellet form. TAZ42018CMX5 provides good performance for jacketing of cables.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific
Uses	• Wire Jacketing
Forms	• Pellets
Processing Method	• Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.48		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	2610	psi	ASTM D638
Tensile Elongation (Break)	200	%	ASTM D638
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	46		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	167	°F	ASTM D794
Brittleness Temperature	5.00	°F	ASTM D746
Aging	Nominal Value	Unit	Test Method
Mechanical Properties After Aging in Air Oven, 212°F, 240 hr			ASTM D638
Change in Tensile Elongation	20	%	
Change in Tensile Strength	10	%	
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	29	%	ASTM D2863

Additional Information

Typical temperature profile for processing SINVICOMP compound is from 160°C to 180°C. The optimum temperatures depend on the type of machine as well as screw design being used to process SINVICOMP.

Feeding zone: 160°C

Compression zone: 160°C~170°C

Mixing zone: 170°C~180°C

Nozzle/Die Zone: 175°C~180°C

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision Date: 3/14/2019

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.