

SCANAMID 6

B12^ F50

Processing data for the injection moulder

| Parameter | Recommended Value | Unit |
|------------------------------------|-------------------|-------------------------|
| Melt temperature | 260-280 | °C |
| Mould temperature | 70-120 | °C |
| Injection pressure | 800-1000 | bar |
| Injection speed | High | |
| Holding pressure | 20-30 | % of injection pressure |
| Back pressure | 5-15 | bar |
| Drying temperature | 75 | °C |
| Drying time in circulation dryer | * | h |
| Drying time in fresh-air dryer | * | h |
| Drying time in dessicant air dryer | * | h |
| Maximum moisture content | 0.1 | % |
| "^" = additive# 0-9 | | |

* Normally supplied in moisture-tight packaging, ready for processing. Opened bag must be pre-dried.

During production stops, emptying the cylinder is recommended. Leave the screw in its front most position. For polycarbonate it is also recommended to leave the cylinder temperature at 160-180°C and that the heating on the feeding zone is on. When producing details in flame retardant material, corrosion protected steel is to recommend for the mould. For further information, see the material safety datasheet (MSDS).