

POLYelast

TPE EDS80 D35

Property	Value	Unit	Standard
Density	0,91	g/cm ³	ISO 1183
MFI at 230°C/2,16kg	7	g/10min	ISO 1133
Hardness Shore D (15 s)	35	Shore D	D2240
Mould shrinkage (with flow)		%	ISO 294-4
Mould shrinkage (across flow)		%	ISO 294-4
Elongation at break		%	ISO 527-2
Maximum tensile strength		MPa	ISO 527-2
Flexural modulus at +23°C		MPa	ISO 178
Notched Charpy at +23°C	25	kJ/m ²	ISO 179
Unnotched Charpy at +23°C		kJ/m ²	ISO 179
Compression set at 72h/23°C		%	DIN 53517
Compression set at 24h/70°C		%	DIN 53517
Abrasion resistance		mg	DIN 53516
Ozone and weather resistance			
Service temperature		°C	

Version 1 1970-01-01

Stated values in this datasheet are approximate. The values originate, if nothing else is stated, from standardised test specimens in natural colour. All information, recommendations and advice given by Polykemi AB or any of its subsidiaries and affiliates, written or verbal, are according to Polykemi AB's knowledge to the date of this edition, correct and given in good faith. It is the responsibility of the customer to test and evaluate if the material suits the application and the environment in which it is intended to be used. Polykemi AB, its subsidiaries and affiliates can not be held responsible or liable for any loss incurred through incorrect or faulty use of the products. When producing details in flame retardant material, corrosion protected steel is to recommend for the mould. Polykemi AB takes no responsibility for any printing errors.