

Features Impact modified

Feature	Value	Unit	Testmethod
PHYSICAL PROPERTIES			
Density	0,90	g/cm ³	ISO 1183
MFI at 230°C/2,16kg	3	g/10min	ISO 1133
MECHANICAL PROPERTIES			
Elongation at break	>55	%	ISO 527-2
Elongation at yield	--	%	ISO 527-2
Maximum tensile strength	15	MPa	ISO 527-2
Maximum flexural strength	--	MPa	ISO 178
Flexural modulus at +23°C	450	MPa	ISO 178
IMPACT PROPERTIES			
Impact strength	--	--	--
Notched Charpy at +23°C	NB	kJ/m ²	ISO 179
Notched Charpy at -20°C	NB	kJ/m ²	ISO 179
THERMAL PROPERTIES			
Softening temperature	--	--	--
Vicat 50°C/h at 49,05N (B)	--	°C	ISO 306
Heat Distortion Temperature	--	--	--
HDT 120°C/h at 455kPa (B)	56	°C	ISO 75/1
HARDNESS			
Hardness Shore A (15 s)	88	Shore A	D2240
Hardness Shore D (15 s)	30	Shore D	D2240
ADDITIONAL INFORMATION			
Mould shrinkage (with flow)	0,9-1,1	%	ISO 294-4
Mould shrinkage (across flow)	0,9-1,1	%	ISO 294-4
Ozone and weather resistance	--	--	--
Service temperature	--	°C	--
PROCESS INSTRUCTIONS			
Drying time	2-4	h	--
Drying temperature	70-80	°C	--
Melt temperature	205-250	°C	--
Mould temperature	40-60	°C	--
Peripheral screw speed	650-800	mm/s	--
Back pressure	60-100	bar	--

During production stops, emptying the cylinder is recommended. Leave the screw in its front most position. For polycarbonate it is also recommended to leave the cylinder temperature at 160- 180°C and that the heating on the feeding zone is on. When producing details in flame retardant material, corrosion protected steel is to recommend for the mould. For further information, see the material safety datasheet (MSDS).

Stated values in this datasheet are approximate. The values originate, if nothing else is stated, from standardised test specimens in natural colour. All information, recommendations and advice given by Polykemi AB or any of its subsidiaries and affiliates, written or verbal, are according to Polykemi AB's knowledge to the date of this edition, correct and given in good faith. It is the responsibility of the customer to test and evaluate if the material suits the application and the environment in which it is intended to be used. Polykemi AB, its subsidiaries and affiliates can not be held responsible or liable for any loss incurred through incorrect or faulty use of the products. When producing details in flame retardant material, corrosion protected steel is to recommend for the mould. Polykemi AB takes no responsibility for any printing errors.

Tel: +46 411-170 30 | **Fax:** +46 411-16730 | **E-mail:** info@polykemi.se | **www.polykemi.se**
Polykemi AB, Bronsgatan 8, Box 14, 271 21 Ystad, Sweden