



# Delrin® 500SC NC010

### ACETAL RESIN

Common features of Delrin® acetal resins include mechanical and physical properties such as high mechanical strength and rigidity, excellent fatigue and impact resistance, as well as resistance to moisture, gasoline, lubricants, solvents, and many other neutral chemicals. Delrin® acetal resins also have excellent dimensional stability and good electrical insulating characteristics. They are naturally resilient, self-lubricating, and available in a variety of colors and speciality grades.

Delrin® acetal resin typically is used in demanding applications in the automotive, domestic appliances, sports, industrial engineering, electronics, and consumer goods industries.

Delrin® 500SC is a masterbatch of 20% silicone fluid in Delrin® 500P. It is designed for cube-blending with any grade of Delrin® to provide lubrication to the surface of molded parts.

The below data reflect the properties of a 10% Delrin® 500SC NC010 letdown in Delrin® 500P NC010 blend.

#### Product information

Resin Identification	POM-SD		ISO 1043
Part Marking Code	>POM-SD<		ISO 11469
Typical mechanical properties			
Tensile Modulus	3000	MPa	ISO 527-1/-2
Yield stress	66	MPa	ISO 527-1/-2
Yield strain	21	%	ISO 527-1/-2
Nominal strain at break	40	%	ISO 527-1/-2
Flexural Modulus	2900	MPa	ISO 178
Flexural Stress at 3.5%	75	MPa	ISO 178
Charpy impact strength, 23°C	270	kJ/m²	ISO 179/1eU
Charpy notched impact strength, 23°C	8.5	kJ/m²	ISO 179/1eA
Hardness, Rockwell, M-scale	84		ISO 2039-2
Hardness, Rockwell, R-scale	117		ISO 2039-2
Poisson's ratio	0.37		
Thermal properties			
Melting temperature, 10°C/min	176	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.8 MPa	96	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	158	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel, -40-23°C	100	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, parallel	100	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal, -40-23°C	110	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	110	E-6/K	ISO 11359-1/-2





## Delrin® 500SC NC010

## ACETAL RESIN

Flammability			
FMVSS Class	В		ISO 3795 (FMVSS
Burning rate, Thickness 1 mm	<80	mm/min	302) ISO 3795 (FMVSS 302)
Other properties Density	1410	kg/m³	ISO 1183
Characteristics			
Additives	Release agent		
Additional information			
Injection molding	<b>PROCESSING</b> As a first indication, please use molding parameters of the product with which		

Delrin® 500SC is blended.

Printed: 2025-07-01

Delrin

Page: 2 of 2