

EcoPaXX[®] Q-KG6-FC

PA410-GF30

30% Glass Reinforced, Food Contact Quality

EcoPaXX[®] Q-KG6-FC has excellent processability and surface quality and is safe for use in a broad variety of food contact applications. For detailed statements and information regarding food contact approvals please contact your Envalior representative.

Sustainability

Bio-based

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.6 / *	%	ISO 294-4
Molding shrinkage (normal)	1.1 / *	%	ISO 294-4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	9500 / 7000	MPa	ISO 527-1/-2
Stress at break	170 / 115	MPa	ISO 527-1/-2
Strain at break	4 / 5.8	%	ISO 527-1/-2
Tensile modulus (120°C)	4600 / -	MPa	ISO 527-1/-2
Stress at break (120°C)	85 / -	MPa	ISO 527-1/-2
Strain at break (120°C)	8.2 / -	%	ISO 527-1/-2
Tensile modulus (160°C)	3700	MPa	ISO 527-1/-2
Stress at break (160°C)	70	MPa	ISO 527-1/-2
Strain at break (160°C)	9.4	%	ISO 527-1/-2
Charpy impact strength (+23°C)	80 / 80	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	60 / -	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	11 / 15	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	9 / -	kJ/m ²	ISO 179/1eA

Property Data

EcoPaXX[®] Q-KG6-FC

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Flexural modulus	8500 / 6300	MPa	ISO 178
Flexural strength	260 / 185	MPa	ISO 178
<i>THERMAL PROPERTIES</i>		<i>DRY / COND</i>	
Melting temperature (10°C/min)	250 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	215 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	243 / *	°C	ISO 75-1/-2
<i>ELECTRICAL PROPERTIES</i>		<i>DRY / COND</i>	
Volume resistivity	>1E13 / 2E12	Ohm*m	IEC 62631-3-1
Surface resistivity	- / 1.5E14	Ohm	IEC 62631-3-2
Electric strength	40 / 35	kV/mm	IEC 60243-1
Comparative tracking index	* / 600	V	IEC 60112
<i>OTHER PROPERTIES</i>		<i>DRY / COND</i>	
Humidity absorption	1.5 / *	%	Sim. to ISO 62
Density	1340 / -	kg/m ³	ISO 1183