

Stanyl[®] KS411 B–MB

PA46

Sustainability

Bio-based
Mass balanced

| <i>PROPERTIES</i> | <i>TYPICAL DATA</i> | <i>UNIT</i> | <i>TEST METHOD</i> |
|----------------------------------|---------------------|-------------------|--------------------|
| <i>THERMAL PROPERTIES</i> | | | |
| Melting temperature (10°C/min) | 287 / * | °C | ISO 11357–1/–3 |
| <i>OTHER PROPERTIES</i> | | | |
| Humidity absorption | 3.7 / * | % | Sim. to ISO 62 |
| Density | 1180 / – | kg/m ³ | ISO 1183 |