

# Stanyl® TE250F9

## PA46–GF45 FR(17)

45% Glass Reinforced, Heat Stabilized, Flame Retardant

Stanyl® TE250F9 is an electro-friendly & flame-retarded high heat polyamide that offers excellent creep resistance, strength, stiffness and fatigue resistance especially at high temperatures in combination with cycle-time advantages and excellent flow.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
<b>RHEOLOGICAL PROPERTIES</b>			
	<b>DRY / COND</b>		
Molding shrinkage [parallel]	0.3 / *	%	Sim. to ISO 294-4
Molding shrinkage [normal]	0.9 / *	%	Sim. to ISO 294-4
<b>MECHANICAL PROPERTIES</b>			
	<b>DRY / COND</b>		
Tensile modulus	17000 / 11000	MPa	ISO 527-1/-2
Tensile modulus (120°C)	9000 / –	MPa	ISO 527-1/-2
Tensile modulus (160°C)	7700	MPa	ISO 527-1/-2
Stress at break	200 / 130	MPa	ISO 527-1/-2
Stress at break (120°C)	110 / –	MPa	ISO 527-1/-2
Stress at break (160°C)	90	MPa	ISO 527-1/-2
Strain at break	2.2 / 4	%	ISO 527-1/-2
Strain at break (120°C)	4.5 / –	%	ISO 527-1/-2
Strain at break (160°C)	5.5	%	ISO 527-1/-2
Flexural modulus	15000 / 11000	MPa	ISO 178
Flexural modulus (120°C)	10500	MPa	ISO 178
Flexural modulus (160°C)	9000	MPa	ISO 178
Flexural strength	300 / 250	MPa	ISO 178
Flexural strength (120°C)	230	MPa	ISO 178
Flexural strength (160°C)	200	MPa	ISO 178
Charpy impact strength (+23°C)	65 / 75	kJ/m²	ISO 179/1eU

## Property Data

# Stanyl® TE250F9

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
Charpy impact strength (-30°C)	50 / 50	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	14 / 15	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength (-30°C)	13 / 13	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength (+23°C)	13 / 15	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength (-40°C)	13 / 13	kJ/m <sup>2</sup>	ISO 180/1A

### **THERMAL PROPERTIES**

#### **DRY / COND**

Melting temperature (10°C/min)	295 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	290 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	290 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.45 / *	E-4/°C	ISO 11359-1/-2
Burning Behav. at 1.5 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	1.5 / *	mm	IEC 60695-11-10
UL recognition	Yes / *	-	-
Burning Behav. at 3.0 mm nom. thickn.	V-0 / *	class	IEC 60695-11-10
Thickness tested	3 / *	mm	IEC 60695-11-10
UL recognition	Yes / *	-	-
Relative Temperature Index – electrical	140	°C	UL746B
RTI electrical (Thickness (1) tested)	0.75	mm	UL746B
Thermal Index 5000 hrs	163	°C	IEC 60216/ISO 527-1/-2

### **ELECTRICAL PROPERTIES**

#### **DRY / COND**

Volume resistivity	1E13 / 1E8	Ohm*m	IEC 62631-3-1
Electric strength	30 / 20	kV/mm	IEC 60243-1
Comparative tracking index	250 / -	V	IEC 60112
Relative permittivity (100Hz)	4.3 / 12	-	IEC 62631-2-1
Relative permittivity (1 MHz)	4 / 4.5	-	IEC 62631-2-1

## Property Data

# Stanyl<sup>®</sup> TE250F9

<i>PROPERTIES</i>	<i>TYPICAL DATA</i>	<i>UNIT</i>	<i>TEST METHOD</i>
<b><i>OTHER PROPERTIES</i></b>	<b><i>DRY / COND</i></b>		
Humidity absorption	1.2 / *	%	Sim. to ISO 62
Density	1820 / –	kg/m <sup>3</sup>	ISO 1183