

Stanyl[®] TW278F10

(PA46+PTFE)–GF50

50% Glass Reinforced, Heat Stabilized, Wear and Friction Modified

Stanyl[®] TW278F10 is a friction–modified high heat polyamide that offers excellent creep resistance, strength, stiffness and fatigue resistance especially at high temperatures in combination with cycle–time advantages and excellent flow. TW278F10 has an excellent track–record in gear applications.

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	<i>DRY / COND</i>		
Molding shrinkage [parallel]	0.4 / *	%	Sim. to ISO 294–4
Molding shrinkage [normal]	0.9 / *	%	Sim. to ISO 294–4
MECHANICAL PROPERTIES			
	<i>DRY / COND</i>		
Tensile modulus	16000 / 10700	MPa	ISO 527–1/–2
Tensile modulus (160°C)	8300	MPa	ISO 527–1/–2
Tensile modulus (200°C)	7600	MPa	ISO 527–1/–2
Stress at break	235 / 170	MPa	ISO 527–1/–2
Stress at break (160°C)	120	MPa	ISO 527–1/–2
Stress at break (200°C)	105	MPa	ISO 527–1/–2
Strain at break	2.2 / 3.3	%	ISO 527–1/–2
Strain at break (160°C)	3.4	%	ISO 527–1/–2
Strain at break (200°C)	3.5	%	ISO 527–1/–2
Flexural modulus	12500 / 12000	MPa	ISO 178
Flexural strength	270 / 255	MPa	ISO 178
Charpy impact strength (+23°C)	55 / 85	kJ/m ²	ISO 179/1eU
Charpy impact strength (–30°C)	35 / 65	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	18 / 13	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (–30°C)	11 / 8.5	kJ/m ²	ISO 179/1eA
Izod notched impact strength (+23°C)	18 / –	kJ/m ²	ISO 180/1A

Property Data

Stanyl® TW278F10

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	290 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	285 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	288 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.3 / *	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.3 / *	E-4/°C	ISO 11359-1/-2
OTHER PROPERTIES			
	DRY / COND		
Humidity absorption	1.6 / *	%	Sim. to ISO 62
Density	1690 / -	kg/m³	ISO 1183

Tens. fatigue 8Hz, T, R=0.1,
dry

