

Akulon[®] F132–E1 CRC–MB

PA6

Medium/High Viscosity, Film Extrusion, Nucleated, Lubricated, Food Contact Quality

Sustainability

Mass balanced
Recycled based

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
MATERIAL SPECIFIC PROPERTIES			
Viscosity number	210	cm ³ /g	ISO 307, 1157, 1628
RSV formic acid, 1g/100ml	3.2	—	Envalior Method
Melt Viscosity (260 °C)	1120	Pa s	Envalior Method, 260 °C
Density	1130	kg/m ³	ISO 1183
THERMAL PROPERTIES			
Coeff. of linear therm. expansion (parallel)	0.9	E–4/°C	ISO 11359–1/–2
Spec. heat capacity	1550	J/(kg K)	—
Average spec. heat capacity 20–150 °C	2250	J/(kg K)	
MECHANICAL PROPERTIES (FILM)			
Modulus of elasticity	465	MPa	Envalior Method, 50 mm/min
Stress at yield, parallel	34	MPa	ISO 527–3
Maximum stress, parallel	96	MPa	ISO 527–3
Maximum strain, parallel	350	%	ISO 527–3
Trouser Tear resistance, parallel	32	—	ISO 6383–1
Puncture resistance	1230	J/m	Envalior Method

Akulon® F132–E1 CRC–MB

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Static coefficient of friction	1.4	–	ISO 8295
Dynamic coefficient of friction	0.8	–	ISO 8295
OTHER PROPERTIES (FILM)		VALUE	
Transparency/Clarity	85	%	Envalior Method
Oxygen transmission rate at 23°C/0%r.h.	20	cm³/(m²*d*bar)	DIS 15105–1/–2
Oxygen transmission rate at 23°C/85%r.h.	31	cm³/(m²*d*bar)	DIS 15105–1/–2
Water Vapor Transmission Rate at 23°C/85%r.h.	35	g/(m²*d)	DIS 15106–1/–3
TEST SPECIMEN PRODUCTION (FILM)		VALUE	
Type of extrusion	cast	–	–
Thickness of specimen	0.05	mm	–
Extruder temperature	270	°C	
Die temperature	270	°C	
Chill Roll Temperature	110	°C	

Akulon[®] F132–E1 CRC–MB

Viscosity–shear rate

