

Akulon[®] F223–D B–MB

PA6

Low/Medium Viscosity, General purpose, Injection Molding, Food Contact Quality

Sustainability

Bio-based
Mass balanced

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	1.1 / *	%	ISO 294–4
Molding shrinkage (normal)	1.1 / *	%	ISO 294–4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	3200 / 1000	MPa	ISO 527–1/–2
Nominal strain at break	20 / >50	%	ISO 527–1/–2
Yield stress	87 / 45	MPa	ISO 527–1/–2
Yield strain	4 / 25	%	ISO 527–1/–2
Flexural modulus	2850 / 900	MPa	ISO 178
Flexural strength	120 / 35	MPa	ISO 178
Charpy impact strength (+23°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy impact strength (–30°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	4.5 / 35	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (–30°C)	2.5 / 5	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	60 / *	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	150 / *	°C	ISO 75–1/–2

Akulon® F223–D B–MB

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Coeff. of linear therm. expansion (parallel)	0.9 / *	E–4/°C	ISO 11359–1/–2
Coeff. of linear therm. expansion (normal)	0.9 / *	E–4/°C	ISO 11359–1/–2
Burning Behav. at 1.5 mm nom. thickn.	V–2 / *	class	IEC 60695–11–10
Thickness tested	1.5 / *	mm	IEC 60695–11–10
Burning Behav. at 3.0 mm nom. thickn.	V–2 / *	class	IEC 60695–11–10
Thickness tested	3 / *	mm	IEC 60695–11–10
Oxygen index	26 / *	%	ISO 4589–1/–2
Glow Wire Flammability Index GWFI	900 / –	°C	IEC 60695–2–12
GWFI (Thickness (1) tested)	1.5 / –	mm	IEC 60695–2–12
Glow Wire Flammability Index GWFI	875 / –	°C	IEC 60695–2–12
GWFI (Thickness (2) tested)	0.75 / –	mm	IEC 60695–2–12
Glow Wire Ignition Temperature GWIT	825 / –	°C	IEC 60695–2–13
GWIT (Thickness (1) tested)	1.5 / –	mm	IEC 60695–2–13
Glow Wire Ignition Temperature GWIT	875 / –	°C	IEC 60695–2–13
GWIT (Thickness (2) tested)	1 / –	mm	IEC 60695–2–13

ELECTRICAL PROPERTIES

DRY / COND

Relative permittivity (100Hz)	3.2 / 14	–	IEC 62631–2–1
Relative permittivity (1 MHz)	3 / 4.5	–	IEC 62631–2–1
Dissipation factor (100 Hz)	50 / 3000	E–4	IEC 62631–2–1
Dissipation factor (1 MHz)	150 / 1200	E–4	IEC 62631–2–1
Volume resistivity	1E13 / 1E10	Ohm*m	IEC 62631–3–1
Surface resistivity	– / 1E14	Ohm	IEC 62631–3–2
Electric strength	28 / 20	kV/mm	IEC 60243–1
Comparative tracking index	* / 600	V	IEC 60112

OTHER PROPERTIES

DRY / COND

Water absorption	10 / *	%	Sim. to ISO 62
Humidity absorption	2.8 / *	%	Sim. to ISO 62

Akulon[®] F223–D B–MB

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Density	1130 / –	kg/m³	ISO 1183
MATERIAL SPECIFIC PROPERTIES		DRY / COND	
Viscosity number	132 / *	cm³/g	ISO 307, 1157, 1628