

Akulon[®] K224–G6

PA6–GF30

30% Glass Reinforced

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.3 / *	%	ISO 294–4
Molding shrinkage (normal)	0.9 / *	%	ISO 294–4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	9700 / 6000	MPa	ISO 527–1/–2
Stress at break	185 / 110	MPa	ISO 527–1/–2
Strain at break	3.8 / 7	%	ISO 527–1/–2
Flexural modulus	9200 / 5300	MPa	ISO 178
Flexural strength	290 / 165	MPa	ISO 178
Charpy impact strength (+23°C)	95 / 110	kJ/m²	ISO 179/1eU
Charpy impact strength (–30°C)	75 / 75	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	14 / 25	kJ/m²	ISO 179/1eA
Charpy notched impact strength (–30°C)	11 / 11	kJ/m²	ISO 179/1eA
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	207 / *	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	220 / *	°C	ISO 75–1/–2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E–4/°C	ISO 11359–1/–2
Coeff. of linear therm. expansion (normal)	0.7 / *	E–4/°C	ISO 11359–1/–2
Burning Behav. at 1.5 mm nom. thickn.	HB / *	class	IEC 60695–11–10
Thickness tested	1.5 / *	mm	IEC 60695–11–10
Burning Behav. at 3.0 mm nom. thickn.	HB / *	class	IEC 60695–11–10

Akulon[®] K224–G6

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Thickness tested	3 / *	mm	IEC 60695–11–10
Burning Behav. at 0.75 mm nom. thickn.	HB / *	class	IEC 60695–11–10
Thickness tested	0.75 / *	mm	IEC 60695–11–10
Glow Wire Flammability Index GWFI	700 / –	°C	IEC 60695–2–12
GWFI (Thickness (1) tested)	2 / –	mm	IEC 60695–2–12
Glow Wire Flammability Index GWFI	700 / –	°C	IEC 60695–2–12
GWFI (Thickness (2) tested)	1.5 / –	mm	IEC 60695–2–12
Glow Wire Ignition Temperature GWIT	725 / –	°C	IEC 60695–2–13
GWIT (Thickness (1) tested)	2 / –	mm	IEC 60695–2–13
Glow Wire Ignition Temperature GWIT	725 / –	°C	IEC 60695–2–13
GWIT (Thickness (2) tested)	1.5 / –	mm	IEC 60695–2–13

ELECTRICAL PROPERTIES	DRY / COND		
Relative permittivity (100Hz)	3.5 / 20	–	IEC 62631–2–1
Relative permittivity (1 MHz)	3.3 / 5	–	IEC 62631–2–1
Dissipation factor (100 Hz)	50 / 3000	E–4	IEC 62631–2–1
Dissipation factor (1 MHz)	150 / 1200	E–4	IEC 62631–2–1
Volume resistivity	1E13 / 1E11	Ohm*m	IEC 62631–3–1
Surface resistivity	– / 1E14	Ohm	IEC 62631–3–2
Electric strength	30 / 25	kV/mm	IEC 60243–1
Comparative tracking index	– / 600	V	IEC 60112

OTHER PROPERTIES	DRY / COND		
Water absorption	6.3 / *	%	Sim. to ISO 62
Humidity absorption	1.9 / *	%	Sim. to ISO 62
Density	1350 / –	kg/m³	ISO 1183