

Akulon[®] K224–LG7/E

PA6–GF35

35% Glass Reinforced, UV Stabilized

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES	DRY / COND		
Molding shrinkage (parallel)	0.15 / *	%	ISO 294–4
Molding shrinkage (normal)	1 / *	%	ISO 294–4
MECHANICAL PROPERTIES	DRY / COND		
Tensile modulus	11000 / 7000	MPa	ISO 527–1/–2
Stress at break	195 / 125	MPa	ISO 527–1/–2
Strain at break	3.7 / 7	%	ISO 527–1/–2
Flexural modulus	10700 / 6450	MPa	ISO 178
Flexural strength	305 / 180	MPa	ISO 178
Charpy impact strength (+23°C)	90 / 100	kJ/m ²	ISO 179/1eU
Charpy impact strength (–30°C)	75 / 75	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	14 / 24	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (–30°C)	12 / 12	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES	DRY / COND		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	210 / *	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	220 / *	°C	ISO 75–1/–2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E–4/°C	ISO 11359–1/–2
Coeff. of linear therm. expansion (normal)	0.6 / *	E–4/°C	ISO 11359–1/–2
OTHER PROPERTIES	DRY / COND		
Water absorption	5.9 / *	%	Sim. to ISO 62

Property Data

Akulon® K224–LG7/E

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Humidity absorption	1.8 / *	%	Sim. to ISO 62
Density	1400 / –	kg/m³	ISO 1183