

Akulon[®] K224–PG6 B–MB

PA6–I–GF30

30% Glass Reinforced, Impact Modified

Sustainability

Bio-based
Mass balanced

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.39 / *	%	ISO 294–4
Molding shrinkage (normal)	1 / *	%	ISO 294–4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	8700 / 4750	MPa	ISO 527–1/–2
Stress at break	150 / 105	MPa	ISO 527–1/–2
Strain at break	5 / 10	%	ISO 527–1/–2
Flexural modulus	8500 / 4900	MPa	ISO 178
Flexural strength	250 / 140	MPa	ISO 178
Charpy impact strength (+23°C)	95 / 110	kJ/m²	ISO 179/1eU
Charpy impact strength (–30°C)	100 / 100	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	23 / 43	kJ/m²	ISO 179/1eA
Charpy notched impact strength (–30°C)	15 / 15	kJ/m²	ISO 179/1eA
THERMAL PROPERTIES			
	DRY / COND		
Temp. of deflection under load (1.80 MPa)	200 / *	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	215 / *	°C	ISO 75–1/–2
Coeff. of linear therm. expansion (parallel)	0.2 / *	E–4/°C	ISO 11359–1/–2
Coeff. of linear therm. expansion (normal)	0.9 / *	E–4/°C	ISO 11359–1/–2

Property Data

Akulon® K224–PG6 B–MB

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Burning Behav. at 3.0 mm nom. thickn.	HB / *	class	IEC 60695–11–10
Thickness tested	3 / *	mm	IEC 60695–11–10
Burning Behav. at 0.75 mm nom. thickn.	HB / *	class	IEC 60695–11–10
Thickness tested	0.75 / *	mm	IEC 60695–11–10

ELECTRICAL PROPERTIES	DRY / COND		
Relative permittivity (100Hz)	3.8 / 14	–	IEC 62631–2–1
Relative permittivity (1 MHz)	3.5 / 4.5	–	IEC 62631–2–1
Dissipation factor (100 Hz)	90 / 3000	E–4	IEC 62631–2–1
Dissipation factor (1 MHz)	150 / 1200	E–4	IEC 62631–2–1
Volume resistivity	1E13 / 1E11	Ohm*m	IEC 62631–3–1
Surface resistivity	– / 1E14	Ohm	IEC 62631–3–2
Electric strength	30 / 25	kV/mm	IEC 60243–1
Comparative tracking index	– / 600	V	IEC 60112

OTHER PROPERTIES	DRY / COND		
Water absorption	5.7 / *	%	Sim. to ISO 62
Humidity absorption	1.7 / *	%	Sim. to ISO 62
Density	1320 / –	kg/m³	ISO 1183