

Akulon[®] Ultraflow K–FHGR24

PA6–(GF+GB)30

10% Glass Reinforced, 20% Glass Beads Reinforced, Heat Stabilized, High Flow

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	6000 / 3500	MPa	ISO 527-1/-2
Stress at break	85 / 55	MPa	ISO 527-1/-2
Strain at break	2.5 / 5	%	ISO 527-1/-2
Flexural modulus	4900 / 2300	MPa	ISO 178
Flexural strength	124 / 63	MPa	ISO 178
Charpy impact strength (+23°C)	21 / –	kJ/m ²	ISO 179/1eU
Charpy impact strength (–30°C)	21 / –	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	4 / 6	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (–30°C)	4 / 4	kJ/m ²	ISO 179/1eA
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	190 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	215 / *	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	0.35 / *	E–4/°C	ISO 11359-1/-2
ELECTRICAL PROPERTIES			
	DRY / COND		
Relative permittivity (100Hz)	3.5 / 14	–	IEC 62631-2-1
Relative permittivity (1 MHz)	3.3 / 4.5	–	IEC 62631-2-1
Dissipation factor (100 Hz)	50 / 3000	E–4	IEC 62631-2-1
Dissipation factor (1 MHz)	150 / 1200	E–4	IEC 62631-2-1
Volume resistivity	1E12 / 1E10	Ohm*m	IEC 62631-3-1
Surface resistivity	– / 1E13	Ohm	IEC 62631-3-2

Property Data

Akulon® Ultraflow K–FHGR24

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
Electric strength	35 / 25	kV/mm	IEC 60243–1
Comparative tracking index	350 / 350	V	IEC 60112
OTHER PROPERTIES	DRY / COND		
Water absorption	6.5 / *	%	Sim. to ISO 62
Humidity absorption	1.9 / *	%	Sim. to ISO 62
Density	1350 / –	kg/m³	ISO 1183