

Akulon[®] Ultraflow K–FKMV5 /C

PA6–MD25

25% Mineral Reinforced, Flame Retardant (halogen free), High Flow

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
RHEOLOGICAL PROPERTIES			
	DRY / COND		
Molding shrinkage (parallel)	0.6 / *	%	ISO 294–4
Molding shrinkage (normal)	0.8 / *	%	ISO 294–4
MECHANICAL PROPERTIES			
	DRY / COND		
Tensile modulus	6200 / –	MPa	ISO 527–1/–2
Stress at break	65 / –	MPa	ISO 527–1/–2
Strain at break	1.8 / –	%	ISO 527–1/–2
Charpy impact strength (+23°C)	25 / 20	kJ/m²	ISO 179/1eU
Charpy impact strength (–30°C)	25 / –	kJ/m²	ISO 179/1eU
Charpy notched impact strength (+23°C)	2 / 2	kJ/m²	ISO 179/1eA
Charpy notched impact strength (–30°C)	2 / –	kJ/m²	ISO 179/1eA
THERMAL PROPERTIES			
	DRY / COND		
Melting temperature (10°C/min)	220 / *	°C	ISO 11357–1/–3
Temp. of deflection under load (1.80 MPa)	110 / *	°C	ISO 75–1/–2
Temp. of deflection under load (0.45 MPa)	205 / *	°C	ISO 75–1/–2
Glow Wire Flammability Index GWFI	960 / –	°C	IEC 60695–2–12
GWFI (Thickness (1) tested)	1.5 / –	mm	IEC 60695–2–12
Glow Wire Flammability Index GWFI	960 / –	°C	IEC 60695–2–12
GWFI (Thickness (2) tested)	3 / –	mm	IEC 60695–2–12
Glow Wire Ignition Temperature GWIT	725 / –	°C	IEC 60695–2–13
GWIT (Thickness (1) tested)	1.5 / –	mm	IEC 60695–2–13

Akulon[®] Ultraflow K–FKMV5 /C

PROPERTIES	TYPICAL DATA	UNIT	TEST METHOD
ELECTRICAL PROPERTIES	DRY / COND		
Volume resistivity	>1E13 / –	Ohm*m	IEC 62631–3–1
Surface resistivity	– / >1E15	Ohm	IEC 62631–3–2
Comparative tracking index	* / 600	V	IEC 60112
OTHER PROPERTIES	DRY / COND		
Water absorption	6.2 / *	%	Sim. to ISO 62
Humidity absorption	1.8 / *	%	Sim. to ISO 62
Density	1380 / –	kg/m³	ISO 1183